

# ENCAPSALL SUPER™

## Industrial Protective Coating



### DESCRIPTION

ENCAPSALL SUPER is a very tough, protective, urethane coating that is especially designed for industrial applications, including secondary containment areas, pipelines, valves and transfer pits. Fortified with iron oxide, ENCAPSALL SUPER cures to a rubber-like, waterproof, seamless membrane that possesses exceptional strength and elasticity.

### OUTSTANDING FEATURES

- Can be used over metal, concrete, masonry, brick, rubber, asphalt, wood, tile and other surfaces
- Produces a fully adhered, seamless, high density, waterproofing membrane
- Resistant to attack from most industrial chemicals, gasoline, acids, alkalis, and detergents
- Protects substrate against rust, corrosion and fungal attack
- Will not deteriorate from exposure to UV radiation, bacteria or other environmental conditions
- Easy to apply directly out of the container by brush, roller or airless spray
- Remains flexible, tough and weatherproof at low temperatures
- Highly penetrative and workable

- Rapidly develops high tensile strength and elongation

### APPLICATION

All surfaces to be treated must be clean, dry and free of loose debris, oils, grease and any substance that would interfere with proper bond. A careful inspection of the surface should be made to detect any signs of damage or defects and all repairs should be completed before application of product. Porous surfaces and certain bituminous surfaces require a priming coat. Contact our Technical Department for details and primer recommendations.

ENCAPSALL SUPER may be applied straight from the pail using brush, roller, or spray technique after 2

minutes of slow power stirring. ENCAPSALL SUPER is applied in 2 coats at a thickness of 16 wet mils per coat. Tools may be cleaned after use in any aromatic solvent.

### PRECAUTIONS

Contains solvent and reactive isocyanate groups. It is recommended that proper safety equipment such as rubber gloves and chemical splash goggles be worn when handling this product. Inhalation should be avoided. Persons with known respiratory allergies should avoid exposure to this product. Avoid contact with skin and eyes. In case of contact, flush with large amounts of water for 15 minutes. Do not ingest. If inhaled, swallowed, or in case of eye contact, get immediate medical attention.

SPECIFICATIONS	
<b>Coating Type</b>	Moisture-cure micaceous iron oxide modified urethane
<b>VOC</b>	200 grams/liter
<b>Pot Life</b>	Single component
<b>Shelf Life</b>	12 months
<b>Recommended Thickness</b>	30 mils dry film thickness
<b>Coverage</b>	50 square feet per gallon
<b>Packaging</b>	1 gallon, 5 gallons, and 55 gallons
<b>Color</b>	Black

# ENCAPSALL SUPER™

## Industrial Protective Coating



### LIMITATIONS

Black surfaces tend to absorb heat which is transmitted through the structure. To prevent heat buildup, Andek recommends an application of Silver Film over the ENCAPSALL SUPER. Keep ENCAPSALL SUPER pails away from direct sunlight.

This product is a moisture-curing urethane and is packaged in specially sealed and air excluded drums. If damaged, air and moisture vapor may enter and cause premature curing. Care should be taken to avoid creating part full containers.

### MAINTENANCE

Damaged ENCAPSALL SUPER may be recoated after thorough cleaning and light sanding.

**Keep out of reach of children and pets.**

For additional information, contact the Andek Technical Department.

TECHNICAL DATA		
Moisture Vapor Transmission	8.4 gms/M2/24 hrs (0.715 perms)	ASTM E-96
Tensile - 24 hour cure	256 lbs/square inch	ASTM D-412
Tensile - simulated aging	585 lbs/square inch	ASTM D-412
Elongation - 24 hour cure	400%	ASTM D-412
Elongation - simulated aging	340%	ASTM D-412
Flexibility at Low Temperatures	180° bend @ 20°F	ASTM C-711
Flashpoint	105°F	FTMS 141A(M4293)
Solids Content	90% (B.W.); 93% (B.V.)	ASTM D-1044
Shore 'A' - 24 hour cure	48	ASTM D-2240
Shore 'A' - simulated aging	55	ASTM D-2240
Impact Resistance	4m indentation, no cracking or loss of adhesion	BS3900 Part 3
Weatherometer	No significant effect after 3000 hours	
Cure Time	24 hours @ 70°F (70% R.H.)	

*NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.*

Effective Date: 011/2010

© 2010 Andek Corporation. All right reserved. ANDEK is a registered trademark