

# OZ-CATALYST™

## High Performance Additive



### DESCRIPTION

OZ-CATALYST is a formulated chemical additive containing latent oxazolidone, a revolutionary product that adds tremendous performance and strength characteristics to urethane-based coatings. When added to approved Andek products, it transforms them into denser, more highly crosslinked coatings that are more chemically resistant and capable of curing at any thickness. Fortifying a coating with OZ-CATALYST enables it to overcome even the toughest performance requirements for sealing, waterproofing, and protection.

### OUTSTANDING FEATURES

- Increases crosslink density to provide greater chemical resistance
- Allows curing to proceed throughout any depth or thickness of applied coating
- Improves tensile strength without reducing elongation
- Provides greater puncture resistance
- Accelerates cure rate at low temperatures
- Reduces surface defects caused by hailstones and other invasive precipitation
- Provides the coating with greater resistance to intrusion from birds, rodents, reptiles, and vermin

### APPLICATION

Before use, also read the product data sheet for the product that is being combined with OZ-CATALYST. OZ-CATALYST may be used with POLAROF RAC, ROOFDX SUPER, ENCAPSALL SUPER, or AIM #1. The use of OZ-CATALYST with any other Andek product should only be attempted after thorough consultation with the Andek Technical Department.

Open the container of OZ-CATALYST and determine if it is liquid and free-flowing. If it has been stored for any length of time below 50°F (10°C), it will have crystallized like honey. If so, warm the container gently with an indirect heat source at 100°F (38°C) until the OZ-CATALYST's consistency is thoroughly liquid. Pour an entire quart container of OZ-CATALYST into a 5 gallon pail of Andek coating and stir thoroughly for 3 minutes using an Andek Pro-

Power Mixer or similar, effective mechanical device. After thorough homogeneity has been achieved, let the mixture sit for 2-3 minutes so that trapped air bubbles can rise up and escape from the coating mixture. Then apply the coating, following the instructions on the coating's container label.

### LIMITATIONS

OZ-CATALYST will reduce the pot life of the coating to approximately 6 hours. Although OZ-CATALYST will allow faster curing at low temperatures, do not apply any Andek coating to a frozen, damp or wet surface. OZ-CATALYST should be stored between 50°F (10°C) and 90° (32°) in a dry area away from direct sunlight.

### PRECAUTIONS

READ AND UNDERSTAND THE ENTIRE OZ-CATALYST MATERIAL

SPECIFICATIONS	
Product Type	Latent Oxazolidone
Pot Life	6 hours @ 70°F (21°C)
Shelf Life	12 months
Usage Ratio	1 quart OZ Catalyst per 5 gallons of coating
Packaging	1 quart
Color	Translucent Beige
V.O.C. Content	50 grams/liter

# OZ CATALYST™

## High Performance Additive



FOR THE PRODUCT BEING COMBINED WITH OZ-CATALYST.

This product contains solvents and reactive amines. Keep away from sources of heat, sparks, and flame. Do not get in eyes or on skin or clothing. Wear standard safety equipment such as chemical splash goggles, rubber gloves, coveralls,

and appropriate respirator when handling this product. Inhalation should be avoided. Persons with known respiratory allergies should avoid exposure to this product. In case of contact with eyes or skin, flush thoroughly with plenty of water for at least 15 minutes. If OZ-CATALYST is swallowed, inhaled, or in the event of eye contact, get medical assistance immediately.

For additional information, contact the Andek Technical Department.

**Keep out of reach of children and pets.**

TECHNICAL DATA		
<b>Total Solids (By Volume)</b>	95%	ASTM D-1044
<b>Viscosity (Average @ 70°F)</b>	6,000 cps	ASTM D-446
<b>Flashpoint</b>	Above 100°F	FTMS 141A
<b>V.O.C. Content</b>	50 grams/liter	EPA Method 24

*NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.*

Effective Date: 09/2010

© 2010 Andek Corporation. All right reserved. ANDEK is a registered trademark