

ROOFDX COPPER™

Premium Waterproofing Coating



DESCRIPTION

ROOFDX COPPER is an extremely tough, metallic, rubber-like, waterproofing coating that, being made with copper flakes, has a very attractive copper finish that will actually patina. This remarkable "liquid copper" coating can be used over all common roofing substrates and will give the appearance of copper sheet roofing at a fraction of the cost. Just like copper sheet, ROOFDX COPPER will develop a classic green patina, or may be sealed with Clearcoat 44 to maintain its new appearance.

OUTSTANDING FEATURES

- Can be used over BUR, rubber, copper, aluminum, tin, concrete, wood, masonry and others
- Produces a fully adhered, seamless, high density, waterproofing membrane
- Prevents water soluble ionic transfer that causes corrosion
- Accommodates rapid movement caused by sudden temperature changes
- Totally watertight and unaffected by ponding water
- May be applied to vertical, pitched and horizontal surfaces

APPLICATION

All surfaces to be treated must be clean, dry and free of loose debris

that may interfere with proper bond. Surfaces that have previously been coated should be examined carefully and tested for adhesion to the substrate. This can be accomplished by applying a strip of scotch tape to the coated surface, thoroughly pushed into full contact, then pulled away at a 90° angle. Observe the adhesive surface for any dislodged coating particles. If the tape has pulled away a significant quantity of coating, or if it has loosened the coating from the substrate, the coating should be removed. Loose coating should be thoroughly removed by abrasion, water jetting or other available technique. Some coatings that are firmly bonded but have reticulated (mud cracked) and the edges lifted will need abrading to present a uniform, smooth surface for coating. Some very inert surfaces, such

as epoxy, will require abrading and/or a special primer coat. ROOFDX COPPER is applied straight out of the can after 2 minutes of low speed mechanical stirring. Apply the product using brush, roller or airless spray technique. The product should be applied in 2 coats at an overall rate of 50 square feet per gallon, achieving a wet film thickness of 30 mils or 15 mils per coat. Clean tools and equipment with xylene or toluene before ROOFDX COPPER begins to dry.

PRECAUTIONS

READ THE ENTIRE ROOFDX COPPER M.S.D.S. BEFORE APPLICATION.

Wear safety equipment, such as splash goggles and rubber gloves, when handling this product. Hands should be protected with a barrier

SPECIFICATIONS	
Coating	Ethylene Elastomer
VOC	300 gms/liter
Pot Life	Not applicable
Shelf Life	12 months
Recommended Thickness	20 mils dry film thickness
Coverage	50 square feet per gallon
Packaging	5 U.S. gallon pails
Color	Copper

ROOFDX COPPER™

Premium Waterproofing Coating



cream and cleaned with a proprietary hand cleaner. Avoid contact with skin and eyes. In case of contact with eyes, seek immediate medical attention in addition to flushing. Do not ingest. In case of ingestion, contact a physician immediately.

LIMITATIONS

Do not apply to frozen or saturated surfaces. Cold temperatures will slow down the drying time. Do not apply if precipitation is forecast within 4 hours after application.

For more information, call our Technical Department.

Keep out of reach of children and pets.

TECHNICAL DATA		
Moisture Vapor Transmission	0.12 gms/M2/24 hours (0.01 perms)	ASTM E-96
Tensile Strength	700 psi	ASTM D-412
Elongation at Break	300%	ASTM D-412
Flexibility at Low Temperature	180 deg. bend @ 20°F	ASTM C-711
Flashpoint	105°F	FTMS 141A(M4293)
Shore 'A' Hardness	65	ASTM D-2240
Solids Content	60% (B.W.); 55% (B.V.)	ASTM D-1044
Viscosity Average @ 70°F	4,500 cps	ASTM D-446
Impact Resistance 4mm Indent.	No cracking or loss of adhesion	BS3900 Part 3
VOC Content	300 grams/liter	ASTM D-1044

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.