

BUILDKOTE™

Rubberized Asphalt Coating



DESCRIPTION

BUILDKOTE is a premium, rubberized asphalt coating that is uniquely fortified with specialty elastomers. Far superior to conventional asphalt emulsion products, BUILDKOTE provides a durable, rubbery, waterproof membrane that can be used alone as a protective sealer or as a base coat for POLAROOOF or SILVER FILM. BUILDKOTE can also be used as a flood coat to level and smooth an uneven substrate, such as a stone-encrusted built-up roof.

OUTSTANDING FEATURES

- ✓ Can be used over BUR, metal, concrete, wood, composites, masonry and other surfaces
- ✓ Produces a fully adhered, seamless, high density, waterproofing membrane
- ✓ Increases the effective service life of the substrate
- ✓ Maintains good adhesion and strength, even under ponding water
- ✓ Flows around encrusted gravel to penetrate and seal the substrate
- ✓ May be used below grade to seal exterior basement walls
- ✓ Will accommodate substrate movement and thermal stresses
- ✓ Remains flexible, rubbery and pliable

- ✓ Will not re-emulsify or wash away with rainwater
- ✓ Single component formula means no measuring or mixing

APPLICATION

All surfaces to be coated should be clean, dry and free from oils, grease, or any substance that will interfere with the bond and proper cure of BUILDKOTE. All loose gravel, dust and ponding water should be removed from built-up roofs. Loose felts and blisters should be re-adhered.

BUILDKOTE is applied directly out of the container using a broom or brush directly onto the substrate. Spread the BUILDKOTE evenly, working backward moving from one edge toward the other. Allow BUILDKOTE sufficient time to cure before permitting foot traffic

LIMITATIONS

Do not apply to frozen or saturated substrates. Protect product from freezing. Store between 45°F and 90°F. Store out of direct sunlight.

PRECAUTIONS

It is recommended that standard safety equipment, such as chemical splash goggles and rubber gloves, be worn when handling this product. Avoid contact with skin and eyes. In case of contact with eyes, flush with clear water for 15 minutes and get immediate medical attention. Do not ingest. In case of ingestion, seek immediate medical attention. Use only in well ventilated areas.

Keep out of reach of children and pets.

For additional information, contact the Andek Technical Department

SPECIFICATIONS	
Coating	Rubberized asphalt
VOC	350 gms/liter
Pot Life	Single component
Shelf Life	12 months
Recommended Thickness	40 mils dry film thickness
Coverage	25 square feet/gallon
Packaging	5 gallon and 55 gallon drums
Color	Black

PRODUCT DATA

BUILDKOTE™
Rubberized Asphalt Coating



TECHNICAL DATA		
VOC Content:	350 gms/liter	ASTM D-1644
Viscosity:	10,000 cps	ASTM D-446
Flashpoint:	105° F	FTMS 141A (M4293)
Shore 'A' Hardness:	95	ASTM D-2240



NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.

Effective Date: 02/2009

© 2009 Andek Corporation. All right reserved. ANDEK is a registered trademark

ANDEK CORPORATION · 850 Glen Ave · P.O. Box 392 · Moorestown NJ 08057-0392
Tel 1(800) 800-2844 · Fax (856) 786-0580 · www.Andek.com