

NW 'Z' GRADE™

Synthetic Rubber Deck Coating



DESCRIPTION

NW 'Z' GRADE is a premium quality single component water-proofing coating for concrete decks, walkways, and stairways. It is also used on steel, fiber-glass, and wood decks. It is solvent-based and may be applied in any temperature range. NW 'Z' GRADE is designed for permanent flexibility and toughness, abrasion resistance, and to bridge and move with hairline cracks, and to resist impingement attack. It may be used in marine or industrial situations and in constant submersion conditions.

OUTSTANDING FEATURES

- ✓ Tough and abrasion resistant
- ✓ Its dense molecular network provides a resilient barrier
- ✓ Its elastomeric properties allow it to expand and contract with the substrate
- ✓ Has good flexibility at low temperatures, maintains its strength at higher temperatures
- ✓ Easy to apply and user friendly to insure high quality results
- ✓ Will not attract insects, birds, reptiles or vermin

APPLICATION

Caution! Read this entire data sheet before continuing.

Surfaces must be dry, free of dirt or loose debris, and free of oil, grease, or any substance that would interfere with adhesion. All repairs of damage or defects must be made prior to product application.

NW 'Z' GRADE is applied straight out of the can after 2 minutes of gentle low speed mixing or stirring. Apply the product using brush, roller, or spray technique. If airless spray application is desired, NW 'Z' GRADE should be used with the following equipment specifications: ratio 30:1 or 40:1 and a #35 or larger tip. Apply NW 'Z' GRADE in a smooth, even fashion to achieve a uniform coating thickness in 1 or 2 coats as desired. Allow sufficient ventilation to promote thorough drying between coats and before service. Drying time in well ventilated

circumstances is 12 hours at 70° F (50% R.H.) for 16 mils wet film thickness.

LIMITATIONS

Do not apply to wet or frozen surfaces that are saturated with moisture. Proper surface preparation is important to product performance. Shelf life is 24 months in unopened cans stored indoors. This product is flammable. Keep away from sources of heat, sparks, and flames. Use only EP rated equipment.

MAINTENANCE

NW 'Z' GRADE is re-coatable. If an area becomes damaged, re-coat with NW 'Z' GRADE. Clean tools and equipment with xylene or toluene solvents. Do not allow the solvents to contact NW 'Z' GRADE that has been applied.

SPECIFICATIONS	
Coating Type	Ethylene elastomer
VOC:	420 gms/liter
Pot Life:	Single Component
Shelf Life:	24 months
Recommended Thickness:	20 mils dry film thickness
Coverage:	2 gallons/100 square feet
Packaging:	5 U.S. gallons (standard size)
Color:	White, Gray, Red, Green, Black, or special colors

NW 'Z' GRADE™

Synthetic Rubber Deck Coating



PRECAUTIONS

NW 'Z' GRADE is a solvent-based product. Avoid contact with skin and eyes. In case of contact with skin, wash with soap and water for 15 minutes. For contact with eyes, wash for 15 minutes with clear water and get medical attention. In case of ingestion, do NOT induce vomiting; immediately contact a

Physician. Avoid inhalation of fumes. If aerosol mist is inhaled, immediately seek medical attention. Wear safety goggles, rubber gloves, coveralls, and filter mask when applying NW 'Z' GRADE.

Keep out of reach of children and pets.

TECHNICAL DATA		
Moisture Vapor Transmission	0.01 perms	ASTM D-96
Tensile Strength	2,000 psi	ASTM D-412
Elongation	350%	ASTM D-412
Solids Content	55% (B.W.); 53% (B.V.)	ASTM D-1044
Flashpoint	105°F (closed cup)	FTMS 141A (M4293)
Shore 'A' Hardness	75 degrees	ASTM D-2240
Weatherometer (5,000 hours)	Pass	ASTM G-23
Low Temperature Flexibility	180 deg. Bend (10°F)	ASTM C-711
Density	Approx. 9 lb/gallon	
Viscosity	Approx. 15,000 cps	

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.

Effective Date: 02/2009

© 2009 Andek Corporation. All right reserved. ANDEK is a registered trademark