

RUBBERKOTE 1047™

Waterproof Coating for Wet Roofs



Performance
Coatings & Sealants
Systems

DESCRIPTION

RUBBERKOTE 1047 is a revolutionary waterproofing coating that is uniquely designed to be applied to wet or damp roofs where curing will proceed even underwater! Yet unlike quick patch materials that have a short life expectancy, RUBBERKOTE 1047 is guaranteed to last for five years! RUBBERKOTE 1047 will adhere to all common roofing substrates and is ideal for either instant roof repairs or as a permanent roof coating.

OUTSTANDING FEATURES

- ✓ Can be used over BUR, cap-sheet, modified, steel, aluminum, tin, zinc, concrete, transite and others
- ✓ Will cure underwater regardless of applied coating thickness
- ✓ Produces a fully adhered, seamless, high density, waterproofing membrane
- ✓ Remains flexible, tough, and weatherproof at low temperatures and will not flow at high temperatures
- ✓ Apply straight out of the container by brush or roller
- ✓ Uses DuPont Kevlar® technology to achieve super strength and durability
- ✓ Will not re-emulsify or wash away with water
- ✓ May be used on vertical, pitched and horizontal surfaces and withstands ponding water

Although only minimal preparation is required, all loose material, stones and grease should be removed, together with as much dust, rust and standing water as is reasonably possible. All holes, gaps and joints should be bridged with ROOFAB sandwiched between sufficient RUBBERKOTE 1047 to provide thorough wetting of the roof surface and thorough saturation of the ROOFAB. This is best accomplished by "stippling in" with a brush. RUBBERKOTE 1047 may be applied in 2 coats of 20 wet mils thickness each over capsheet, modified, metal, transite or concrete after the above preparation is complete. The 1st coat may be applied directly over any fresh, wet repairs as curing will proceed regardless of thickness although slower. The 2nd coat may be applied as soon as the 1st coat is sufficiently dry to walk on (normally 2-3 days at 65°F). Care should be taken

not to disturb any patches or pre-treatments as they may still be wet. RUBBERKOTE 1047 may be applied over asphalt or coal tar B.U.R. after the preparation described above has been completed. The 1st coat should be applied at 66 square feet per gallon; ROOFAB laid into it and thoroughly "stippled in" by brush with a 2nd coat at 66 square feet per gallon to remove all tents and voids. The Roofab should be overlapped as indicated by the lap lines and thoroughly saturated with RUBBERKOTE 1047 so that no dry spots remain.

LIMITATIONS

Not recommended in areas of high chemical attack (around stacks, etc.).

MAINTENANCE

Damaged areas may be repaired by re-application of RUBBERKOTE 1047.

SPECIFICATIONS	
Coating	Resin-based, air drying
VOC	400 gms/liter
Pot Life	Single component
Shelf Life	12 months
Recommended Thickness	30 mils dry film thickness
Coverage	30 - 40 square feet per gallon
Packaging	3.5 gallon pails
Color	Light Gray

RUBBERKOTE 1047™

Waterproofing Coating for Wet Roofs



PRECAUTIONS

Contains solvents. Read M.S.D.S. thoroughly before using. Do not get on skin or in eyes. Do not ingest or inhale vapor. Make sure that vapor does not enter building. If skin is contaminated, use suitable cleaner. If eyes are contaminated, wash with water and seek

medical attention. If ingested, do NOT induce vomiting and seek immediate medical attention. If inhaled, remove person to fresh air.

CAUTION: KEEP OUT OF REACH OF CHILDREN AND PETS.

TECHNICAL DATA		
Moisture Vapor Transmission	.32 perms	ASTM E-96
Tensile Strength	250 psi	ASTM D-412
Elongation	65%	ASTM D-412
Flexibility at Low Temperature	180 deg. bend @ -20°C	ASTM C-711
Shore 'A' Hardness	36	ASTM D-2240
Puncture Resistance	50 psi	ASTM D-154-79
Viscosity at 70°F	10,000 cps	ASTM D-446
Solids Content	60% (B.W.); 58% (B.V.)	ASTM D-1044
Drying Time @ 80°F (70% R.H.)	60 hours (to walk on)	
Total Cure @ 80°F (70% R.H.)	7 days (to 36 deg. Shore 'A')	
Application Equipment	Brush, roller or spray	
Cleaning of Equipment	Mineral Spirits	

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.

Effective Date: 02/2009

© 2009 Andek Corporation. All right reserved. ANDEK is a registered trademark