

# POLAROOF RAC™

## Urethane Waterproofing Coating



Performance  
Coatings & Sealants  
Systems

### DESCRIPTION

POLAROOF RAC is a single component urethane, modified with bright aluminum flakes and fire retardant chemicals. It is especially designed as a waterproofing membrane for all kinds of roofing. POLAROOF RAC is tough and elastic with a high tensile strength and good puncture resistance, and contains corrosion-inhibiting pigments for protection against rust and acid rain. POLAROOF RAC is approved by Underwriters Laboratories® (UL) and Factory Mutual Research Corporation® (FM).

### OUTSTANDING FEATURES

- ✓ Can be used over BUR, single-ply, metal, concrete, foam, wood, primed composites, masonry and others
- ✓ Produces a fully adhered, seamless, high density, waterproofing membrane
- ✓ Protects substrate against rust, corrosion, UV damage and acid rain
- ✓ Easy to apply directly out of the container by brush, roller or airless spray
- ✓ May be used on vertical, pitched and horizontal surfaces and withstands ponding water
- ✓ Lightweight membrane does not require removal old roofing materials, saving time and money

- ✓ Produces a waterproof surface that will not be deteriorated by fungal growth or algae
- ✓ Remains flexible, tough and weatherproof at low temperatures and will not flow at high temperatures
- ✓ Rapidly develops high tensile strength
- ✓ Will not re-emulsify or wash away with rainwater
- ✓ Will not become brittle and crack with age
- ✓ Can be easily recoated

### APPLICATION

Surfaces must be dry, free of dirt, loose debris, oils, grease or any substance that could interfere with adhesion. Refer to the Polaprime data sheet for information regarding selection of appropriate primer if necessary. Application over seams in metal roofs is achieved by embedding

4" or 6" wide ROOFAB into a fresh coat of RAC applied at 15 mils wet thickness. The fabric is then saturated with a second application at sufficient thickness to remove all voids, fishmouths and dry spots. Bolt-heads on metal roofs should be daubed with sufficient RAC that they are encapsulated to the point of rundown. As soon as the POLAROOF RAC has dried, it may be coated with RAC or other compatible top-coat. Application over E.P.D.M., modified and other rubber roofs requires the preparation detailed above, including reinforcement of seams. Some rubbers will swell slightly immediately upon application. This is normal, the adhesion process is complete when the original dimensions have returned. New urethane foam should receive 2 coats of RAC at 15 mils wet thickness per coat to be sure that no foam is exposed to pinholes or holidays. Previously

SPECIFICATIONS	
<b>Coating</b>	Moisture-cure
<b>VOC</b>	200 gms/liter
<b>Pot Life</b>	Single component
<b>Shelf Life</b>	12 months
<b>Recommended Thickness</b>	30 mils dry film thickness
<b>Coverage</b>	2 to 3 gallons per 100 square ft
<b>Packaging</b>	1 gallon, 5 gallon, and 55 gallon containers
<b>Color</b>	Bright Silver

# POLAROOF RAC™

## Urethane Waterproofing Coating



produce a mottled, dull appearance that is not detrimental to its overall performance. POLAROOF RAC should never be applied to a wet or damp surface, or pinholes may result.

### LIMITATIONS

Shelf life is 12 months in unopened cans. Part-full cans should be avoided. Storage must be out of direct sunlight at below 90°F to avoid skinning.

### MAINTENANCE

Damaged areas may be repaired by cleaning surface and application of POLAROOF RAC as described in Application section.

### PRECAUTIONS

Contains solvent and reactive isocyanates. Read MSDS thoroughly before using. Do not get on skin or in eyes. Do not ingest or inhale vapor.

Make sure that vapor does not enter building. If skin is contaminated, use suitable cleanser; if eyes are contaminated, wash with water for 15 minutes and seek medical attention. If clothing is contaminated, discard. If ingested, do NOT induce vomiting and seek medical attention. If inhaled, remove person to fresh air.

**KEEP AWAY FROM CHILDREN AND PETS.**

TECHNICAL DATA		
<b>Moisture Vapor Transmission</b>	1.57 perms	ASTM E-96
<b>Tensile Strength</b>	600 psi	ASTM D-412
<b>Elongation</b>	500%	ASTM D-412
<b>Flexibility at Low Temperatures</b>	180° bend @ -10° C	ASTM C-711
<b>Shore 'A' Hardness</b>	56 degrees	ASTM D-2240
<b>Surface spread of flame</b>	Class 1	ASTM E-108
<b>Puncture Resistance</b>	120 psi	ASTM D-154-79
<b>Viscosity at 70°F</b>	4,500 cps	ASTM D-446
<b>Drying Time @ 80°F (70% R.H.)</b>	24 hours (to walk on)	
<b>Total Cure @ 80°F (70% R.H.)</b>	72 hours (to 56 deg. Shore 'A')	
<b>Solids Content</b>	82% (B.W.); 94% (B.V.)	ASTM D-1044
<b>Application Equipment</b>	Brush, roller or spray	
<b>Cleaning of Equipment</b>	Xylene or Aromatic Naptha	

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.

Effective Date: 02/2009

© 2009 Andek Corporation. All right reserved. ANDEK is a registered trademark

**ANDEK CORPORATION** · 850 Glen Ave · P.O. Box 392 · Moorestown NJ 08057-0392  
Tel (800) 800-2844 · Fax (856) 786-0580 · www.Andek.com