

K-CATALYST™

Thickening and Reinforcing Agent



DESCRIPTION

K-CATALYST is an aramid fiber that may be added to approved Andek coatings to boost viscosity and adjust the rheological behavior to individual application requirements. K-CATALYST will thicken the coating to a paste or caulk-like consistency, enabling the coating to be used for repairs, preparation work and other activities that require a thickened material. K-CATALYST may be added in precise measured amounts to achieve the intended characteristics required by the applicator.

OUTSTANDING FEATURES

- Provides the exact coating application control demanded by the professional applicator
- Allows exact color matching of detail and reinforcement material with the entire coating application
- Provides rheological adjustment to improve film thickness yield on steep pitch profiles
- Reacts rapidly to achieve target viscosity
- Maintains excellent "wet edge" to accurately transition-in patched areas
- Provides reinforcement and added strength to the modified coating

APPLICATION

Before use, also read the product data sheet for the product that is being combined with K-CATALYST. By order of the United States Government, this product must not be used for any illegal or military purpose, or be exported to any prohibited country. K-CATALYST may be used with POLAROOFF RAC, ROOFDX SUPER, POLAROOFF NW, ENCAPSALL SUPER, NW Z GRADE, AIM#1, AIM #2, AIM #3 and POLAFLOOR EPOXY TOPPING. The use of K-CATALYST with any other Andek product should only be attempted after thorough consultation with the Andek Technical Department.

Add approximately ½ of a 1 pound unit of K-CATALYST into a 5 gallon pail of Andek coating and stir thoroughly and vigorously for at least 3 minutes, using an Andek ProPower Mixer or similar effective

mechanical device. The K-CATALYST is microscopically similar to a mass of tight springs that need to be pulled apart with high shear mixing to achieve maximum performance. After thorough homogeneity has been achieved, let the mixture sit for approximately 3 to 5 minutes. This will allow trapped air bubbles to rise up and escape from the mixture and for the associative thickening effect to develop. If the viscosity is still not sufficient for the purpose required, additional K-CATALYST may be added and the above procedure repeated until the target rheology is achieved. Then apply the mixed coating, following the instructions on the coating's container label.

LIMITATIONS

K-CATALYST will reduce the pot life of the following products to six hours: POLAROOFF RAC,

(CONTINUES)

SPECIFICATIONS	
Product Type	Aramid Fiber
Pot Life	Variable (See Limitations Section)
Shelf Life	1 year from date of manufacture
Usage Ratio	Variable (see Application Section)
Packaging	1 pound unit
Appearance	Fluffy yellow powder
V.O.C. Content	Negligible

PRODUCT DATA

K-CATALYST™

Thickening and Reinforcing Agent



ROOFDX SUPER, ENCAPSALL SUPER and AIM #1. The pot life of the following products will be unaffected by the addition of K-CATALYST: POLAROOFF NW, NW Z Grade, AIM #2, AIM #3 and POLAFLOOR EPOXY TOPPING. A powerful mixer is essential for best results. Keep K-CATALYST dry, as it is ineffective if wet.

PRECAUTIONS

Read the container label warning and Material Safety Data Sheet (MSDS) for important health and safety information prior to the use of this product.

Keep out of reach of children and pets.

For additional information, contact the Andek Technical Department

TECHNICAL DATA	
Chemical Type	Aramid Fiber
Physical Form	Fibrous Powder
Total Solids	100%
Specific Gravity	0.9
V.O.C. Content	Zero grams/liter

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.

Effective Date: 11/2014

© 2014 Andek Corporation. All right reserved. ANDEK is a registered trademark

ANDEK CORPORATION · 850 Glen Ave · P.O. Box 392 · Moorestown NJ 08057-0392
Tel 800.800.2844 · Fax 856.786.0580 · www.Andek.com