

# COCOON 501™

## Air Barrier Coating



### DESCRIPTION

COCOON 501 is formulated for interior surfacing of masonry, plywood, steel, etc. COCOON 501 is a liquid polyvinyl chloride coating which can be sprayed on any clean, dry building surface. Wherever it is sprayed, it forms a tough, strong permanent waterproof skin that is adaptable to most surfaces. COCOON 501 seals against moisture, gases, corrosion, and particulates, and maintains excellent low temperature flexibility.

### OUTSTANDING FEATURES

- Highly efficient seal for interior applications such as dust-free areas, shower rooms, brewery fermentation rooms and bottling plants, hospital scrub rooms, and natatoriums
- Provides abrasion resistance, washability, moisture protection, chemical resistance, and bacteria resistance
- Resists corrosion and surface deterioration caused by acids, oils, fats, greases, and fungi
- Maintains an effective gas seal coating in controlled atmosphere storage, hyperbaric suites, and fumigation warehouses
- Effectively seals plenum chambers and ducts in environmental control systems against air loss
- Bridging characteristics provide a permanent seal around lights, filters, pipe and duct penetrations, and at all ceiling and wall joints

### APPLICATION

CAUTION! Read this entire data sheet before continuing. All surfaces must be dry, free of dirt, loose debris, oil, grease, or any substance that could interfere with adhesion. Additionally, all surfaces should be modified in a manner to make them as smooth as possible by removing sharp projections and filling gaps and voids. A minimum surface profile of ½ mm should be maintained for maximum adhesion. After proper masking, prime the entire surface to be coated with Vinyl Bond B, directly from the can, by spray or roller, and allow the primer to dry. Close all penetrations through the surface by using a webbing coat. Webbing solution is made by mixing 1 part Webbing

Agent with 3 parts COCOON 501 and mix until the color is uniform. Spray apply COCOON 501 in multiple overlapping passes until a 20 mil dry film thickness has been achieved. The first should be very light to avoid breaking the webs. Properly applied, the coating should be free of voids and pinholes. Voids and pinholes must be re-sprayed to achieve a complete seal. Prior to the removal of any protection or equipment, a thorough inspection of the entire area should be completed, and all damage or deficiencies must be repaired and re-sprayed. All termination joints should be sealed with a polyurethane sealant. For recommendations regarding equipment, contact our Technical Department.

SPECIFICATIONS	
Coating Type	Polyvinyl Chloride Solution
VOC	254 gms/liter
Pot Life	Single Component
Shelf Life	2 years from date of manufacture
Recommended Thickness	3 to 5 mils d.f.t. per coat
Coverage	1 gallon per 100 sq. ft. per coat x 4 coats
Packaging	5-gallon pails
Colors	Clear, White, and other normal colors

# COCOON 501™

**Corrosion-Resistant Coating**



**LIMITATIONS**

Proper ventilation must be provided during application for effective drying of the coating, and all applicators must wear suitable respirators.

**MAINTENANCE**

Damaged areas may be repaired by cleaning surface and application of COCOON 501 as described in the Application Section.

**PRECAUTIONS**

Read and understand the Material Safety Data Sheet thoroughly. Make sure that all involved parties are familiar with the M.S.D.S. COCOON 501, in its liquid state, is flammable, and proper safety precautions against exposure to open flame, sparks, or other sources of ignition must be taken and strict safety rules enforced.

**Keep out of reach of children and pets.**

For more information, call our Technical Department.

TECHNICAL DATA		
<b>Moisture Vapor Transmission</b>	0.06 perms	ASTM E-96
<b>Tensile Strength</b>	900 psi	ASTM D-412
<b>Elongation</b>	170%	ASTM D-412
<b>Flexibility at Low Temperature</b>	180 deg. bend @ -30°C	ASTM C-711
<b>Shore 'A' Hardness</b>	75 degrees	ASTM D-2240
<b>Weatherometer (240 hours)</b>	85 gloss	ASTM G-23
<b>Viscosity</b>	55 ku	ASTM D-446
<b>Drying Time</b>	5 minutes per coat	
<b>Total Solids</b>	30% (B.W.); 25% (B.V.)	ASTM D-1044
<b>Flashpoint</b>	+15°F	FTMS 141A (M4293)
<b>Fire Resistance</b>	Self-extinguishing	
<b>Cleaning of Equipment</b>	M.E.K. or Acetone	

*NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.*

Effective Date: 11/2012

© 2012 Andek Corporation. All right reserved. ANDEK is a registered trademark