

# RUBBERKOTE 1047™

## All Weather Repair Coating



Performance  
Coatings & Sealants  
Systems

### DESCRIPTION

RUBBERKOTE 1047 is a revolutionary waterproofing coating that is uniquely designed to be applied to wet or damp roofs where curing will proceed even underwater! Yet unlike quick patch materials that have a short life expectancy, RUBBERKOTE 1047 is guaranteed to last for five years! RUBBERKOTE 1047 will adhere to all common roofing substrates and is ideal for either instant roof repairs or as a permanent roof coating.

### OUTSTANDING FEATURES

- Can be used over BUR, capsheet, modified, steel, aluminum, tin, zinc, concrete, transite and others
- Will cure underwater regardless of applied coating thickness
- Produces a fully adhered, seamless, high density, waterproofing membrane
- Remains flexible, tough, and weatherproof at low temperatures and will not flow at high temperatures
- Apply straight out of the container by brush or roller
- Uses DuPont Kevlar® technology to achieve super strength and durability
- Will not re-emulsify or wash away with water
- May be used on vertical, pitched and horizontal surfaces and withstands ponding water

- Will not stain coatings applied over it

### APPLICATION

Although only minimal preparation is required, all loose material, stones and grease should be removed, together with as much dust, rust and standing water as is reasonably possible. Bird excrement, algae and slime mold should be scrubbed off of the surface for best adhesion results. All holes, gaps and joints should be bridged with ROOFAB sandwiched between sufficient RUBBERKOTE 1047 to provide thorough wetting of the roof surface and thorough saturation of the ROOFAB. This is best accomplished by "stippling in" with a brush. RUBBERKOTE 1047 may be applied in 2 coats of 20 wet mils thickness each over capsheet, modified, metal, transite or concrete after the above preparation is complete. The 1<sup>st</sup> coat may be

applied directly over any fresh, wet repairs as curing will proceed regardless of thickness although slower. The 2<sup>nd</sup> coat may be applied as soon as the 1<sup>st</sup> coat is sufficiently dry to walk on (normally 2-3 days at 65°F). Care should be taken not to disturb any patches or pre-treatments as they may still be wet. RUBBERKOTE 1047 may be applied over asphalt or coal tar B.U.R. after the preparation described above has been completed. The 1<sup>st</sup> coat should be applied at 66 square feet per gallon; ROOFAB laid into it and thoroughly "stippled in" by brush with a 2<sup>nd</sup> coat at 66 square feet per gallon to remove all tents and voids. The Roofab should be overlapped by at least 2 inches and thoroughly saturated with RUBBERKOTE 1047 so that no dry spots remain.

### LIMITATIONS

Not recommended in areas of high  
(CONTINUES)

SPECIFICATIONS	
Coating	Air drying, thermoplastic rubber
VOC	400 grams/liter
Pot Life	Not applicable (single component)
Shelf Life	2 years (unopened) from date of manufacture
Recommended Thickness	30 mils dry film thickness
Coverage	Approx 30 to 40 square feet per gallon, depending upon substrate
Packaging	1 and 3.5 US gallon pails
Color	Light Gray

PRODUCT DATA

# RUBBERKOTE 1047™

## All Weather Repair Coating



Performance  
Coatings & Sealants  
Systems

chemical attack (around stacks, etc.). RUBBERKOTE 1047 does contain solvent so H.V.A.C. equipment should be prevented from drawing air from the rooftop during application.

### PRECAUTIONS

Read the container label warning and Safety Data Sheet (SDS) for important health and safety information prior to the use of this product.

For additional information, contact our Technical Department.

### MAINTENANCE

Damaged areas may be repaired by re-application of RUBBERKOTE 1047.

**Keep product out of reach of children and pets.**

TECHNICAL DATA		
Moisture Vapor Transmission	.32 perms	ASTM E-96
Tensile Strength	250 psi	ASTM D-412
Elongation	65%	ASTM D-412
Flexibility at Low Temperature	180 deg. bend @ -20°C	ASTM C-711
Shore 'A' Hardness	36 degrees	ASTM D-2240
Puncture Resistance	50 psi	ASTM D-154-79
Viscosity at 70°F	10,000 cps	ASTM D-446
Solids Content	60% (B.W.); 58% (B.V.)	ASTM D-1044
Drying Time @ 80°F (70% R.H.)	60 hours (to walk on)	
Total Cure @ 80°F (70% R.H.)	7 days (to 36 deg. Shore 'A')	
Application Equipment	Brush, roller or spray	
Cleaning of Equipment	Mineral Spirits	

*NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.*

Effective Date: 1/2015

© 2015 Andek Corporation. All right reserved. ANDEK is a registered trademark

**ANDEK CORPORATION** · 850 Glen Ave · P.O. Box 392 · Moorestown NJ 08057-0392  
Tel 800.800.2844 · Fax 856.786.0580 · www.Andek.com